

IKONOS PROFIFLEX PRO MPT FX100+ DB140

PRODUCT DESCRIPTION:

Series of Ikonos Profiflex Pro MPT FX100+ DB140 includes a white, matt (MPT FX100+) monomeric, calandered, self-adhesive PVC with removable, transparent modified with 12% tackifier, dispersion of polyacrylate adhesive. **Original ink receptive coating is dedicated for waterbased pigment inks.** The product was intentionally designed as an eco-friendly solutions for printing in high-speed and top-quality.

Reduce your carbon footprint by using MPT FX100+ DB140. Print Photo quality images with water-based inks. By using this technology for your reproductions you take care of our planet. Our production process does not cause VOC (volatile organic compounds) emission.

PRODUCT STRUCTURE:

Coating: Special Ink Receptive Layer: 15g/m² (±5g/m²)
 Film: 90 µm, monomeric, calandered, white , matt PVC film
 Adhesive: removable modified with 12% tackifier, transparent dispersion of polyacrylate 25g/m² (±2g/m²) - dry
 Liner: One-side siliconized, 135 g/m² , CCK type backing paper with Ultra Stable Technology

Ink Receptive layer - 15g/m ² (±5g/m ²)
90 µm, white PVC film
Adhesive
Liner

COMPATIBLE INKS:

Waterbased Pigment Inks¹

RANGE OF APPLICATION:

Ikonos Profiflex Pro MPT FX100+ DB140 is perfect for all indoor applications. It enables the fast-printing, with usage of eco-friendly waterbased pigment inks and it suits well for large quantity production.

PRINTING SIDE: Outside

PHYSICAL FEATURES:

	STANDARD NO.	VALUE
Thickness ² of PVC	ISO 2286-3	90 µm (±5µm)
Coating weight		15g/m ² (±5g/m ²)
Total thickness ² (coating + film + glue + liner)	ISO 2286-3	235 µm (±5%)
Total weight³		288g/m ² (±5%)
Surface gloss⁴	DIN 67 530	< 5GU
Tensile stress at break	ISO 527-3/2/200	32 MPa [MD] 28 MPa [CD]
Tensile strain at break	ISO 527-3/2/200	80% [MD] 200% [CD]
Adhesive Power⁵		
Initial	FINAT 9	12.2 N/25 mm
After 20 min	FINAT 1	11.7 N/25 mm
After 24 h	FINAT 1	13.4 N/25 mm
Temperature range		
While applying	-	from 10°C to 35°C
While exploiting	-	from -15°C to 50°C
Durability*	90° vertical exposure	indoor up to 2 years (unprinted)
Shelf Life	2 years (in original packaging, at 20 °C and 50% relative humidity)	

¹ The customer is obliged to conduct his own tests before the final application, to verify the compatibility of this product with the desired result.

² Mitutoyo MDE-25PX

³ KERN PNJ

⁴ Micro-tri-gloss, BYK Altana, Measurement at 60°

⁵ Shimadzu Autograph AGS-x

DURABILITY

The data concerns vertical surface exposure of an unprinted/unprocessed film. The outdoor durability relates to the temperate climate of Middle Europe. If the film is exposed to extreme weather conditions, such as austere insolation, high UV radiation or humidity it may undergo accelerated deterioration. PVC film may also weaken in greatly contaminated areas and regions of high altitude.

HANDLING & PROCESSING

Recommended storage conditions: 50% of relative humidity, 20 °C, in original packaging.

Customer should always store rolls together with label which consist information about type of product, dimensions of roll and batch number.

Any claims or requests will not be accepted without information about batch number.

During storage time shrinking of the edges of monomeric PVC film could be noticed.

To obtain good print quality/good processing results we recommend acclimatize rolls in printing/processing room min. 24 hour before printing/processing. Large fluctuations in temperature and humidity between the room and the material have an impact on flatness and printability of material.

If printed, the ink must be perfectly dry before further processing e.g laminating or application. Features of products could be changed by the residuals solvents. The surface on which product is applied must be free of dust, grease, lubricant and any other substances which may hinder the film from adhesion.

Due to wide range of possible uses and applications customers should independently verify the appropriateness of material for their explicit purpose, prior to use. The customer is obliged to conduct his own tests before the final application, to verify the compatibility of this product with the desired result.

IMPORTANT NOTICE

The information included in the present publication is based upon our knowledge as well as practical experience and can be changed without prior notice. All information always represents an average, a minimum or maximum value and should be considered as such.

This data is displayed only in order to serve as a source of information and is given without guarantee and does not constitute a warranty.

All presented information refers to unprinted/unprocessed Ikonos products. Features of products could change after printing/processing due to this reason all printed/processed Ikonos products are not covered by warranty.

Our limited liability relates only to the cost of the defective material which was bought by customer.

Agents, representatives and salesmen are not entitled to give any guarantee, warranty or representation other to the foregoing.

Ikonos shall not be held responsible for any damage to substrates, surfaces or machines resulting from the use or removal of Ikonos product, nor shall Ikonos be held responsible for any consequential damage.

All Ikonos products sold are subject to "General conditions of sales and delivery" (<http://ikonosmedia.eu/download/>).

Ikonos shall not be held responsible for any incidental or consequential damage, including, but not limited to, loss of profit or income, labour cost, costs or expenses for reproducing graphics, loss of production time, costs for removing defective graphics, etc.

All rights reserved. All trademarks and registered trademarks are the property of their respective owners. August 2016.